

Tidal

| | |
|----------------------------|---|
| Content | 100% Nylon Fiber Matrix |
| Width | 54 inch/137 cm |
| Weight | 8.8 oz/sq yd, 300 g/m ² |
| Thickness | 28 mils; 0.7 mm |
| Cleanability Code | S/W |
| Wear | 100,000+ double rubs Wyzenbeek Wire screen (ASTM D-4157- 82) * |
| Crock | Wet 5/Dry 5 (AATCC-8-1988) |
| Trap Tear Strength | 30 lbs. x 30 lbs. (ASTM D-1117-80) |
| Grab Tensile Strength | 100 lbs. x 100 lbs. (ASTM D-5034-90) |
| Seam Strength | 100 lbs. x 100 lbs. (ASTM D-1683-90A) |
| Colorfastness: Gas Fumes | (AATCC-23, 3 cycles) Class 4-5/Little to no color change |
| Colorfastness: I | <ul style="list-style-type: none">• Fadeometer Test (AATCC-16A-90, 100 hrs.) Class 5/ No color change• Weather-O-Meter (Xenon Arc, SAE J1885), 225kj/m2: Little to no color change |
| Colorfastness: II | Sulfide Staining (ASTM D-1712-89) No staining |
| Flammability Class I | UFAC/NFPA 260-1989 |
| Flammability Pass | California Technical Bulletin 117-2013 Section 1 – Pass |
| Flammability Class A Rated | Tunnel Test: (ASTM E84) ** |
| Flame Compatibility | Furniture upholstered with Destiny and constructed with other suitable components can comply with Cal 133. Can also be treated to meet many international flammability codes. |

*Failure in Wyzenbeek abrasion was defined as wear to expose the microfiber.

**Tested as NYTEK with sheeting backing by adhered method.